

## NP510A TECHNICAL DATA BULLETIN

GRADE: NP510A NEMA LI 1-1998 Grade: FR-4 U.L. LISTED: Y <sup>2</sup>

DESCRIPTION: NP510A is a woven glass fabric composite combined with epoxy resin system. This material contains bromine on the epoxy resin backbone. NP510A is certifiable to MIL-I-24768/27, Type GEE-F, ANSI/NEMA IM 60000-2021 Grade FR-4, IEC 60893-3-2 PE GC 202, ASTM D709 Type FR-4 and IPC 4101/21.

#### **TYPICAL PROPERTIES**

				VALUE			
			UNITS	Thickness Tested			
				0.0625"	0.125"	0.500"	
PHYSICAL PROPERTIES							
Specific Gravity							
(ASTM D792)			1			1.85	
Rockwell Hardness							
(ASTM D785)	0.250" Build-up		M Scale	98			
Moisture Absorption							
(ASTM D570)	Condition D <sub>1</sub> -	24/23	%	0.10			
Flexural Strength	Condition A		psi	65,000 / 52,000			
(ASTM D790)		LW / CW	(MPa)	(448.2) / (358.5)			
Flexural Modulus	Condition A		kpsi	2,900 / 2,600			
(ASTM D790)		LW / CW	(GPa)	(20.0) / (17.9)			
Tensile Strength	Condition A		psi		40,000 / 32,000		
(ASTM D638)		LW / CW	(MPa)		(275.8) / (220.6)		
Izod Impact Strength	Condition A		ft-lb/in				
(ASTM D256)		LW / CW	(J/cm)				
	Condition E-4	18/50	ft-lb/in			7.90 / 7.30	
		LW / CW	(J/cm)			(4.22) / (3.90)	
Compressive Strength	Condition A		psi			66,000	
(ASTM D695)		Flatwise	(MPa)			(455.1)	
Bonding Strength	Condition A		lb			2,300	
(ASTM D229)			(kg)			(1,043.3)	
Shear Strength	Condition A		psi	21,500			
(ASTM D732)		Perpendicular	(MPa)	(148.2)			



### TECHNICAL DATA BULLETIN

GRADE: NP510A NEMA LI 1-1998 Grade: FR-4 U.L. LISTED: Y<sup>2</sup>

#### **TYPICAL PROPERTIES (continued)**

			VALUE Thickness Tested			
		UNITS				
			0.0625"	0.125"	0.500"	
THERMAL PROPERTIES						
Temperature Index 1	Florida di / Monto di cital	°C		100 / 110		
	(UL Bulletin 746b) Electrical / Mechanical		130 / 140			
Coefficient of Thermal Expansion		"/"/°C		100/120		
(IPC-TM 650-2.4.24) Tg by DMA	X-axis / Y-axis	x10 <sup>-6</sup>		10.0 / 13.0		
I g by DMA		°C			130	
Flammability Vertical (UL Bulletin 94)	Condition A	Class	V-0			
ELECTRICAL PROPERTIES		0.0.00				
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-				
	Condition D-24/23	-	0.032			
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-				
	Condition D-24/23	-	4.80			
Breakdown Voltage (ASTM D149)	Condition A	kVolts	66			
	Condition D-48/50	kVolts	65			
Electric Strength (ASTM D149)	Condition A	Volts/mil	630			
		(kV/cm)	(248.0)			
	Condition D-48/50	Volts/mil	670			
Arc Resistance	Condition A	(kV/cm)	(263.8)			
(ASTM D495)	Condition /	sec		130		

<sup>&</sup>lt;sup>1</sup> This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, <a href="https://www.norplex-micarta.com">www.norplex-micarta.com</a>, to determine if the information is the most current available

Specification writers: Contact Norplex-Micarta for specification values before submission.

<sup>&</sup>lt;sup>2</sup> Only applies to thicknesses greater than 0.029".



# NP510A TECHNICAL DATA BULLETIN

**GRADE**: NP510A IEC 60893-3-2-EP GC 202 U. L. LISTED: Y

**DESCRIPTION:** NP510A is a woven glass fabric composite combined with epoxy resin system. It is engineered to provide NEMA grade FR-4 properties. This material contains bromine on the epoxy resin backbone. NP510A is certifiable to MIL-I-24768/27, Type GEE-F.

**THICKNESS TESTED:** 1.59mm, 3.18mm & 12.70mm

#### TYPICAL PROPERTIES

PHYSICAL PROPERTIES	UNITS	VALUE	
Moisture Absorption (1.59mm) (IEC 60893-2/8.2)	Condition A	mg	8.30
Flexural Strength (1.59mm) (IEC 60893-2/5.1)	Condition A LW / CW	Мра	480 / 390
<b>Izod Impact Strength</b> (12.7mm) (IEC 60893-2/5.4.3)	Condition A LW / CW	kJ/m²	58 / 55
Charpy Impact Strength (12.7mm) (IEC 60893-2/5.4.2)	Condition A LW / CW	kJ/m²	63 / 50
THERMAL PROPERTIES			
Flammability Vertical (1.59mm) (IEC 60893-2/7.2)	Condition A	Class	V-0
ELECTRICAL PROPERTIES			
Breakdown Voltage (3.18mm) (IEC 60893-2/6.1)	Condition A	kVolts	65
Electric Strength (1.59mm) (IEC 60893-2/6.1)	Condition A	kV/mm	25
Insulation Resistance (3.18mm) (IEC 60893-2/6.3)	Condition E-24/50; D-24/23	МΩ	3.33E+13

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, <a href="https://www.norplex-micarta.com">www.norplex-micarta.com</a>, to determine if information is most current available.

Specification writers: Contact Norplex-Micarta for speciation values before submission.

Norplex-Micarta Page 1 of 1 6/14/2023